Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 22/06/2020

Lab ID	:	**CP-2020-07-11-21**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-06-20
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	22/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	15/06/2020	22/06/2020	150.92 X 149.91 X 151.68	22624	**8.922**	413.8	18.3	18.2
2	PCC	M20	15/06/2020	22/06/2020	151.16 X 149.41 X 151.95	22584	**8.645**	409.4	18.1	
3	PCC	M20	15/06/2020	22/06/2020	151.34 X 151.86 X 149.35	22982	**8.584**	417.4	18.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-07-11-21 **Date: 13/07/2020**

: Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

: Project Sub Division, BBMP, Bangalore.

: Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town

: Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64

: EE(Project)/Ynk Zone/WO/10/2020-21

: Sample supplied by Agency

: Satisfactory

: 17-06-20

: PCC

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 13/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
PCC	M20	15/06/2020	13/07/2020	149.06 X 149.62 X 149.05	22302	**8.594**	523.7	23.5	23.3
PCC	M20	15/06/2020	13/07/2020	150.09 X 150.59 X 151.30	22602	**8.237**	508.1	22.5	
PCC	M20	15/06/2020	13/07/2020	151.89 X 151.22 X 149.29	22970	**8.457**	550.5	24.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 22/06/2020

Lab ID	:	**CP-2020-07-11-21**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-06-20
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	22/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	15/06/2020	22/06/2020	150.38 X 151.22 X 151.18	22740	**8.922**	419.5	18.4	18.5
2	PCC	M20	15/06/2020	22/06/2020	149.12 X 149.45 X 151.51	22285	**8.645**	420.5	18.9	
3	PCC	M20	15/06/2020	22/06/2020	151.17 X 149.90 X 149.64	22660	**8.584**	412.5	18.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 13/07/2020

Lab ID	:	**CP-2020-07-11-21**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-06-20
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	13/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	15/06/2020	13/07/2020	151.46 X 149.31 X 150.61	22615	**8.594**	536.1	23.7	23.2
2	PCC	M20	15/06/2020	13/07/2020	149.90 X 149.62 X 149.67	22428	**8.237**	507.0	22.6	
3	PCC	M20	15/06/2020	13/07/2020	150.53 X 151.73 X 151.06	22839	**8.457**	533.0	23.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 22/06/2020

Lab ID	:	**CP-2020-07-11-21**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-06-20
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	22/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	15/06/2020	22/06/2020	149.44 X 149.45 X 149.25	22334	**8.922**	422.1	18.9	18.6
2	PCC	M20	15/06/2020	22/06/2020	151.51 X 151.96 X 150.82	23023	**8.645**	437.4	19.0	
3	PCC	M20	15/06/2020	22/06/2020	150.36 X 150.18 X 149.04	22581	**8.584**	406.6	18.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-07-11-21** **Date: 13/07/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town

Agency : Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64

Customer's Reference : EE(Project)/Ynk Zone/WO/10/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-06-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	15/06/2020	13/07/2020	152.00 X 150.34 X 151.77	22850	**8.594**	536.5	23.5	23.3
2	PCC	M20	15/06/2020	13/07/2020	151.02 X 149.54 X 150.50	22583	**8.237**	515.7	22.8	
3	PCC	M20	15/06/2020	13/07/2020	149.92 X 150.08 X 150.51	22499	**8.457**	527.6	23.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 14-05-20

Lab ID	:	CP-2020-07-11-21
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-05-20
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	12-05-20
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : CP-2020-07-11-21

Date: 14-05-20

PHYSICAL PROPERTIES

SLno	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.58	–
2	Specific Gravity	2.57	–
3	Material finer than 75 micron(%)	6.8	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

QC ABSTRACT

NAME OF WORK: Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Brick	Compressive Strength	One Test		1	1
		WATER ABSORPTION	One Test		1	1
		EFFLORESCENCE	One Test		1	1
		DIMENSIONS AND TOLERANCES	One Test		1	1
6	PCC(M20)	Compressive Strength(7days and 28days)	3 set /16-30 cum	22.08	6	6
7	WMM	Sieve Analysis	One Test		1	1
		Impact Value	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
8	Mortar Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		Compacted Bulk Density	One Test		1	1
		Loose Bulk Density	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1
9	Plaster Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-07-11-21** **Date: 15-05-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-05-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	13-05-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.08	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.5	225m^2/kg, Min
3	Density (gm/cc)	3.14	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	145 minutes	Not less than 30 minutes
6	Final Setting time	275 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-07-11-21** **Date: 10-06-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-05-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	13-05-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-07-11-21** **Date: 15-05-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer's Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	12-05-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-05-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	189	189	1.3	98.7	90-100
3	20 mm	7284	7473	49.8	50.2	30-70
4	10 mm	4089	11562	77.1	22.9	10-35
5	4.75 mm	3001	14563	97.1	2.9	0-5
6	Pan	437	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-07-11-21** **Date: 15-05-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.5	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.8	
3	Specific Gravity	2.66	–
4	Bulk Density(Loose) (Kg/l)	1.42	–
5	Bulk Density(Compacted) (Kg/l)	1.48	–
6	Water Absorption(%)	0.21	–

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-07-11-21** **Date: 14-05-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Public Toilets at Parks in Ward No.04 Yelahanka New Town
Agency	:	Sri.K.S Chowda Reddy, No.32, 3rd Main, 3rd Cross, Maruthinagara Yelahanka, Bangalore-64
Customer Reference	:	EE(Project)/Ynk Zone/WO/10/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-05-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-05-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	199	199	4.0	96.0	90-100
3	10 mm	3050	3249	65.0	35.0	25-55
4	4.75 mm	1502	4751	95.0	5.0	0-10
5	Pan	249	5000	100	0	–

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-07-11-21** **Date: 14-05-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.7	
3	Specific Gravity	2.62	_
4	Bulk Density(Loose) (Kg/l)	1.48	_
5	Bulk Density(Compacted) (Kg/l)	1.55	_
6	Water Absorption(%)	0.27	_
7	Aggregate crushing Value(%)	23.9	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.1	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |